

# StrataGrid™

StrataGrid™ er en geonettarmering for jord. Disse høyytelses geonettene er konstruert av strikket polyestergarn med høy molekylvekt og høy strekkstyrke med et beskyttende belegg. StrataGrid™ er konstruert for å være mekanisk og kjemisk holdbar, både i den tøffe installasjonsfasen og i aggressive jordmiljøer.



	Unit	SGi 40	SGi 60	SGi 80	SGi 100	SGi 120	SGi 150	SGi 180	SGi 200	SGi 250	SGi 300	SGi 350	SGi 400	
<b><u>Mechanical properties</u></b>														
<b>Tensile strength</b> (ASTM D 6637 – Method A)	MD	kN/m	40	60	80	100	120	150	180	200	250	300	350	400
	CMD	kN/m	20	20	30	30	30	30	30	30	30	30	30	30
<b>Creep reduction factor</b> (at 20°C, 114 years design life)			1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47
<b>Creep limited strength</b>	MD	kN/m	27.2	40.8	54.4	68.0	81.6	102.0	122.4	136.1	170.1	204.1	238.1	272.1
<b>Partial factor - installation damage</b> (ASTM D 5818)														
In clay, silt or sand			1.07	1.07	1.07	1.07	1.07	1.04	1.04	1.04	1.04	1.04	1.04	1.04
<b>Partial factor - environmental effects</b> (GRI-GG7, GRI-GG8)														
Environment, $4 \leq \text{pH} \leq 8$			1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10
<b><u>Molecular properties</u></b>														
<b>Molecular weight</b> (GRI GG8)	g/mol		min. 25,000											
<b>Carboxyl End Group (CEG)</b> (GRI GG7)	mmol/kg		max. 30											
<b><u>Physical properties</u></b>														
<b>Roll dimensions</b> (width x length)	m		3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100	3.8x100
<b>Roll area</b>	sqm		380	380	380	380	380	380	380	380	380	380	380	380

Roll weights are average values including shipping cores. Actual roll weights may vary.  
The properties might change at the time of manufacturing, storing, handling or shipping  
The above values are subject to change as per discretion of the company

Registered office:  
Sabnam House, Plot No. A-15/16  
Central Cross Road B MIDC Andheri (E)  
Mumbai 400 093  
T: + 91 22 4063 5100 I F: +91 22 4063 5199

E: info@strataindia.com | W: www.strataindia.com  
India. USA . Brazil. Ireland  
CIN: U17299MH2004PTC148625



14  
GR 14/91510

Manufacturing unit:  
62 – 64, Silver Industrial Estate,  
Patalia Road, Bhimpore, Daman,  
UT – 396210, India  
T: + 91 0260 2220160